

Marque de/Brand of/Merk van

Sycobois France sa, Ceve nv

Origine/Origin

Chine/China

**Composition/Samenstelling**

Contreplaqué/Veneer/Fineer :	Sapeli FSC	
Qualité/Quality/Kwaliteit	+B/BB	
Cœur/Core/Kern :	Eucalyptus – bois dur/hardwood/hardhout	
Colle/Glue/Lijm :	WBP/E1	(EN314-2)

Utilisation/Use/Gebruik

Usage externe humide/Humid outdoor use/Vochtig Buitenshuis gebruik	(EN636-3)
Usage interne humide/Humid indoor use/Vochtig Binnenhuis gebruik	(EN636-2)

Caractéristiques/Specifications/Kenmerken

Ébullition/Boilproof/Kooktest:	+24h/u	
Résistance à l'eau/Waterresistance:	Colle/Glue/Lijm WBP	
Densité/Density/Densiteit:	580kg/m ³	(EN323)
Humidité/Humidity/Vochtigheid:	<12% (EN-322)	(EN322)
Dimension Tolérance/Tolerance/Tolerantie:	±0.5mm	
Déformation/Warp/Werken	<1%	
Élasticité longitudinalement/longitudinally:	35-45N/mm ²	(EN310)
Élasticité longitudinalement/longitudinally:	32-35N/mm ²	(EN310)

Dimensions/Dimensions/Afmetingen (stock)

Standard 2500x1220mm:	3.6/5/8/10/12/15/18/21/25/30/35/40mm	(EN324-1)
XLarge 3050x1530mm:	5/8/10/12/15/18/21/25/30/35/40mm	(EN324-1)

* scier sur demande/sawing on demand/zaagwerk op aanvraag

Écologie/Ecology/Ecologie

EUTR-conforme	100% Sylviculture durable/Durable forestry
CARB-conforme	Émission contrôlée/Controlled emission
FSC/PEFC	Sur demande/On demand/Op aanvraag

Certificats/Certificaten

EUTR, CARB, CE+, PSA

